

# WELDOX® 900

## Data sheet

### HIGH STRENGTH STRUCTURAL PLATE

WELDOX 900 is a general structural steel with a minimum yield strength of 900 MPa. WELDOX 900 meets the requirements on the corresponding steel grades and qualities according to EN 10025.

#### Applications

Load carrying structures having very high demands on low weight.

#### Designation

WELDOX 900D with guaranteed impact toughness at -20° C (-4°F). Corresponds to S890Q

WELDOX 900E with guaranteed impact toughness at -40° C (-40°F). Corresponds to S890QL

WELDOX 900F with guaranteed impact toughness at -60° C (-76°F). Corresponds to S890QL1

#### Chemical Composition

(ladle analysis)

C*	Si*	Mn*	P	S	B*	Nb*	Cr*	V*	Cu*	Ti*	Al*	Mo*	Ni	N
max	max	max	max	max	max	max	max	max	max	max	total min	max	max	max
%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
0,20	0,50	1,60	0,020	0,010	0,005	0,04	0,70	0,06	0,30	0,04	0,018	0,70	0,10	0,015

\*Intentional alloying elements. The steel is grain-refined

Plate thickness	CEV	
	Typical values	
	%	%
8 mm	0,55	0,36
20 mm	0,55	0,36
60 mm	0,55	0,36

$$CEV = C + \frac{Mn}{6} + \frac{Cr+Mo+V}{5} + \frac{Ni+Cu}{15}$$

$$CET = C + \frac{Mn+Mo}{10} + \frac{Cr+Cu}{20} + \frac{Ni}{40}$$

#### Mechanical Properties

Plate thickness mm	Yield strength <sup>1)</sup> R <sub>p0,2</sub> , min MPa <sup>2)</sup>	Tensile strength <sup>1)</sup> R <sub>m</sub> MPa <sup>2)</sup>	Elongation <sup>1)</sup> A <sub>5</sub> min %
4,0 - 50,0	900	940-1100	12
50,1- 80,0	830	880-1100	12

<sup>1)</sup> For transverse test pieces

<sup>2)</sup> 1 MPa = 1 N/mm<sup>2</sup>

# WELDOX 900

## Data sheet

### Impact Properties

Steel grade and quality	Impact energy for (J) tests on transverse <sup>1)</sup> and Charpy V 10 x 10 tests specimens <sup>2)</sup>			
	Test temperatures in °C			
	0	-20	-40	-60
WELDOX 900 D	30	27	-	-
WELDOX 900 E	35	30	27	-
WELDOX 900 F	40	35	30	27

<sup>1)</sup>Unless otherwise agreed, transverse impact testing according to EN 10025 option 30 will apply.

<sup>2)</sup>For plate thicknesses less than 12 mm subsize Charpy V-specimens are used. The specified minimum value is then proportional to the cross section of the specimen.

### Testing

Testing according to EN 10025.

### Delivery Condition

Q Quenched and tempered as per EN 10025-6

### Dimensions

WELDOX 900 is supplied in plate thicknesses of 4-80 mm.

More detailed information on dimensions is provided in our brochure 042-UK-General Product Information WELDOX, HARDOX and ARMOX.

### Tolerances

- All plates are produced with AccuRollTech™ thickness precision guarantee.

AccuRollTech™ meets the requirements of EN 10 029, but offers more narrow tolerances.

- Tolerances on flatness according to Class N (Normal tolerances).

More detailed information is given in our brochure 042-UK General Product Information WELDOX, HARDOX and ARMOX or at [www.weldox.com](http://www.weldox.com).

### Surface Condition

According to EN 10163-2, Class A, Subclass 1 (repair by welding is allowed).

### General Technical Delivery Requirements

According to our brochure 042-UK General Product Information WELDOX, HARDOX and ARMOX.

### Heat Treatment and Fabrication

WELDOX 900 has obtained its mechanical properties by a quenching and tempering process.

WELDOX 900 is not suited for applications requiring hot working at temperatures above 550°C since the material may then lose its guaranteed properties.

For information concerning welding and fabrication, see our brochures on [www.weldox.com](http://www.weldox.com) or consult our Technical Customer Service.

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on the product. Grinding, especially of primer coated plates, may produce dust with high particle concentration.